



# PRODUCT INFORMATION

## Rust+ RESCUE™ 200

Stellar Solutions, Inc.  
4511 Prime Parkway  
McHenry, IL 60050  
Phone (847) 854-2800  
Fax (847) 854-2830  
stellar@citrisurf.com  
www.citrisurf.com

### Technical Data:

**Description:** *Rust Rescue 200* is a high quality blend of chemicals formulated for the protection of stainless steel and other metal surfaces in conjunction with *CitriSurf* passivation, especially in environments where moisture and harsh atmospheric chemicals are expected to or have lead to corrosion.

### Physical Properties:

Chemical Composition	Calcium sulfonate, proprietary ingredients
Operating Temperature	70-90°F
Flash Point	150°F
Normal working concentration	Use as received

**Packaging:** 1 quart, 1 gallon, 55 gallon metal containers.

**Application Procedure:** Remove any existing rust first with a rust remover such as *CitriSurf 77 Plus* or *CitriSurf 2310*, using the procedure recommended for that product. Then allow surface to dry completely before applying *Rust Rescue*. All equipment, mixers, applicators or pumps should be clean and dry prior to use.

**Prior to use, mix thoroughly by shaking or stirring.** Apply a light coat of *Rust Rescue 200* to the surface to be protected with a clean soft cloth, sprayer, brush or roller. Coverage is approximately 800 square feet per gallon. Wait approximately 2 to 3 minutes and then wipe off the excess product. Allow the surface to dry completely in air. Drying can be accelerated by use of a hot air oven or other drying medium such as an air blower (hair dryer).

**Notes on Use:** Although very safe in normal use, *Rust Rescue 200* is a Calcium Sulfonate based material, and as such it may cause irritation to exposed surfaces of the body for some persons. **See Safety Data Sheet before using this material.** Rubber or plastic gloves should be worn to apply the product to the surface or to wipe it dry.

page 2...

**Disposal:** Dispose of according to all federal, state and local regulations.

**Storage:** *Rust Rescue 200* should be stored at temperatures between 50°F and 120°F in steel or aluminum containers.

**Technical Services:** For technical assistance, please contact Stellar Solutions at (847) 854-2800.

**Testing of your products with *Rust Rescue* before using in production is recommended. Every product and production facility is different, and requires testing to ensure that *Rust Rescue* is compatible with the particular situation. No warranty is implied, or may be given in writing or verbally without the written permission of Stellar Solutions, Inc.**

04/2018

CitriSurf and Stellar Solutions are registered trademarks of Stellar Solutions, Inc., McHenry, IL, USA